

RE-SNTAN TBL

Multipurpose Phenolic Syntan

FEATURES

Property	Value
Appearance	White Powder
Bases	Phenol Condensate
Active Substance	96-+1
Ph	3,0-4,0 10%Sol.
Lightfastness	Good light fastness
Shelf Life	18-24 months in original container
Bisphenol S	<60ppm
Bisphenol F	<20ppm

CHARACTERISTICS

- *Completely miscible with water.
- *Maximum filling effect especially loose belilies and flanks..
- *It is suitable for every kind of soft leathers such sheep-goat-cow-buffalo.
- *Very suitable buffed and nubuck articles gives very good evennes of the nappa or suede.
- *Suitable for White and pale colours it acts as a humectant to assist leather in holding moisture.

APPLICATION

FILLER F It is normally applied in the fatliouing bath 20-30 minutes before fatliouir addition. Where the synthetic and vegatable tannings are used together RE-SNTAN STF can be used in the same bath assisting vegetable penetration and distribution to the leather. Generally we suggest to apply 3-4 % on the shaved weight. Gives better dye distribution of the leather without compromising the colour. The quantity we suggest 3-4 % on the shaved weight.