RE-SNTAN BBK

Phenolic, Synthetic Polymer and Tannin Filling Blend

FEATURES

Appearance	Beige coloured powder
Active Substance	98 ± 2
pH	5,5 ± 0,5
Shelf Life	12 months in original container

CHARACTERISTICS

*Does not affect color uniformity.

*Provides a compact fiber structure without causing grain looseness.

*Produces a fine grain structure.

*Easily dispersible in water.

*Specially formulated for chrome retanning.

APPLICATION

RE-SNTAN BBK can be used alone or in combination with other natural extracts, syntans, and resins for the retanning of chrome-tanned or vegetable-tanned leathers.

It should be applied during the filling stage after neutralization. The recommended dosage ranges from **3% to 12%** based on shaved weight, depending on the leather size, thickness, and origin.

The combination of **Acryl R-150** and **Re-sntan BBK** provides full-bodied leather with a very tight and round grain structure.

Retanning

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.